

1072 HT Paint Spray, Thermo Paint

Ver.: 2021-8

Description

Heat-resistant special paint in aerosol designed to protect surfaces exposed to high temperatures up to 600 °C/1112 °F (exhaust, engine parts etc.).


Features & Benefits

- excellent adhesion to different metal substrates
- temperature resistant up to 600 °C/1112 °F
- anti-corrosion protection
- high covering power.

Substrate preparation

Clean, dry, and degrease the surface with a suitable anti silicone cleaner. Thoroughly sand and sandblast respectively; the surface has to be blank to the bare metal!

Application data



Mixing ratio

The product is ready to use!



Application

Shake can thoroughly until the mixing balls move freely (2 min).

Number of coats	2 coats
Spraying distance	20 – 25 cm
Flash-off	1 - 2 min

Important: the thinner the paint coat is applied the better is the temperature resistance and adhesion. No primer needed. The best results is achieved at the application on bare metal! It is strongly recommended that ready for use product is applied at a temperature higher than 20 °C/68 °F.

After spraying turn the can upside down and spray until the valve is clean.



Drying

Dust dry (20 °C/68 °F)	10 min
Touch dry (20 °C/68 °F)	60 min

1072 HT Paint Spray, Thermo Paint

Ver.: 2021-8

Prod. Nr.	Description	Volume	Packaging Box
1072-A-0,5	Silver	500 ml	12 pcs
1072-B-0,5	Black	500 ml	12 pcs

VOC

2004/42/II B(e)(840)624

Shelf life

Max. 24 months from the production date under normal storage conditions and unopened can.

Additional Information

FOR PROFESSIONAL USE ONLY!

Always read the instructions.

IMPORTANT: This product contains hazardous substances at work, so it is necessary to always use/wear appropriate protective equipment. For further instructions, check the label on the product and safety data sheet. A person who uses the product for any purpose other than recommended in this technical data sheet, acts at his own risk. It is the user's responsibility to take all necessary steps to fulfil the local legislation.

Materials described are designed for application by professional, trained personnel using proper equipment and are not intended for sale to the general public.

Information and methods described are based on the best information and practices known to us and serve merely as guidelines for optimal use, without liability to performance, results, or fitness for any intended use. We do not accept any responsibility for the behaviour of the product or damage arising from the use of the product. Before using the product, the user must check if this is the latest version.

All products mentioned in this data sheet are trademarks owned by Silco.