

Description

Quick drying, over-paintable underbody protection against corrosion, stone chips, salt, noise etc.


Features & Benefits

- strong adhesion on raw or galvanized metal or old underbody protection
- elasticity, durability
- builds protective film against stone chips, salt, noise etc.
- regulation of structure with pressure and distance
- quick drying

Substrate preparation

Surfaces to be treated must be clean and dry, rust-free and grease-free.
Do not coat the exhaust, brake systems or motor parts.

Application data



Mixing ratio


The product is ready to use! Shake the product before use!



Application

Number of layers:	min 2
Flash off:	3-5 min
Distance:	15-30 cm
Single layer thickness:	0,15-0,25 mm of wet film
Temperature range:	apply between 10 °C/50 °F and 25 °C/77 °F
Dry film thickness:	250-400 microns

Before overpainting the stone chip protection should be completely dry.
We recommend scuffing the surface with grit P600 before overpainting to improve adhesion.

	Overpaintable at 10 °C/50 °F 90-120 min at 20 °C/68 °F 60-90 min at 30 °C/86 °F 45-60 min
	Storage Dry, ventilated place away from direct exposure to sunlight Storage temperature: 10 – 30°C (50 – 86 °F)

Complementary products

Application gun (Prod. Nr. 2006)

Prod. Nr.	Description	Volume	Packaging Box
2030-A-1	White	1 kg	12
2030-B-1	Black	1 kg	12
2030-C-1	Grey	1 kg	12

VOC

(2004/42/II B(e)(840)410

Shelf life

Min. 12 months from the production date under normal storage conditions and unopened can.

Additional Information

FOR PROFESSIONAL USE ONLY!

Always read the instructions.

IMPORTANT: This product contains hazardous substances at work so it is necessary to always use/wear appropriate protective equipment. For further instructions, check the label on the product and safety data sheet. A person who uses the product for any purpose other than recommended in this technical data sheet, acts at his own risk. It is the user's responsibility to take all necessary steps to fulfil the local legislation.

Materials described are designed for application by professional, trained personnel using proper equipment and are not intended for sale to the general public.

Information and methods described are based on the best information and practices known to us and serve merely as guidelines for optimal use, without liability to performance, results or fitness for any intended use. We do not accept any

responsibility for the behaviour of the product or damage arising from the use of the product. Before using the product, the user must check if this is the latest version.

All products mentioned in this data sheet are trademarks owned by Silco.