

## CARFIX UNIVERSAL SOFT PUTTY 210

Ver.: 2020-5

### Features & Benefits

- very easy to spread
- non-porous, smooth surface
- easy sanding

### Substrate preparation

Surfaces to be treated must be clean, dry, rust-free and grease-free. Optimal adhesion can be achieved on well abraded surface.

### Application data

---

#### Mixing ratio

210 Carfix Universal Soft                    100 (parts by weight)  
 Putty hardener                                2 – 3 % (do not overdose)

Mix the putty and hardener thoroughly until the colour is even. Do not overdose! Excessive quantity of hardener can cause colour change on the topcoat. Hardener amount below 2 % can extend the drying time.

#### Application

Usage temperature                            min 10 °C/50 °F

#### Drying

Time to sand (20 °C/68 °F)                20 – 25 min  
 Potlife (20 °C/68 °F)                        4 – 5 min

#### Sanding

Only dry sanding  
 First sanding                                    P80-120  
 Re-sanding                                        P120-P320

Prod. Nr.	Description	Volume	Packaging
210-1,8	(hardener included)	1,8 kg	6

### VOC

---

VOC 2004/42/IIB(b) (250)67

### Shelf life

---

Min. 12 months from the production date under normal storage conditions and unopened can.

### Additional Information

---

FOR PROFESSIONAL USE ONLY!

Always read the instructions.

IMPORTANT: This product contains hazardous substances at work so it is necessary to always use/wear appropriate protective equipment. For further instructions, check the label on the product and safety data sheet. A person who uses the product for any purpose other than recommended in this technical data sheet, acts at his own risk. It is the user's responsibility to take all necessary steps to fulfil the local legislation.

Materials described are designed for application by professional, trained personnel using proper equipment and are not intended for sale to the general public.

Information and methods described are based on the best information and practices known to us and serve merely as guidelines for optimal use, without liability to performance, results or fitness for any intended use. We do not accept any responsibility for the behaviour of the product or damage arising from the use of the product. Before using the product, the user must check if this is the latest version.

All products mentioned in this data sheet are trademarks owned by Silco d.o.o..