

Description

Quick-drying, cathode protection against corrosion with excellent long-term effects. Contains 99 % pure zinc.




Features & Benefits

- protection of scratches and welding points
- corrosion protection of galvanized surfaces
- resistance to salt water
- conductive intermediate layers in spot welding.

Substrate preparation

Clean, dry, and degrease the surface.

Application data

	<p>Mixing ratio The product is ready to use!</p>								
	<p>Application Shake can thoroughly until the mixing balls move freely (2 min).</p> <table data-bbox="347 1227 957 1406"> <tr> <td>Number of coats</td> <td>2 – 3 coats</td> </tr> <tr> <td>Spraying distance</td> <td>20 – 25 cm</td> </tr> <tr> <td>Flash-off</td> <td>2 - 3 min</td> </tr> <tr> <td>Dry film thickness</td> <td>20 – 30 micron</td> </tr> </table> <p>It is strongly recommended that ready to use product is applied at a temperature higher than 20 °C/68 °F.</p>	Number of coats	2 – 3 coats	Spraying distance	20 – 25 cm	Flash-off	2 - 3 min	Dry film thickness	20 – 30 micron
Number of coats	2 – 3 coats								
Spraying distance	20 – 25 cm								
Flash-off	2 - 3 min								
Dry film thickness	20 – 30 micron								
	<p>Drying</p> <table data-bbox="347 1671 1045 1794"> <tr> <td>Dust dry (20 °C/68 °F)</td> <td>8 - 10 min</td> </tr> <tr> <td>Touch dry (20 °C/68 °F)</td> <td>20 - 30 min</td> </tr> <tr> <td>Recoatible (20 °C/68 °F)</td> <td>48 h</td> </tr> </table>	Dust dry (20 °C/68 °F)	8 - 10 min	Touch dry (20 °C/68 °F)	20 - 30 min	Recoatible (20 °C/68 °F)	48 h		
Dust dry (20 °C/68 °F)	8 - 10 min								
Touch dry (20 °C/68 °F)	20 - 30 min								
Recoatible (20 °C/68 °F)	48 h								

Prod. Nr.	Description	Volume	Packaging Box
4020-0,5	Zinc	500 ml	12 pcs

VOC

2004/42/IIB(e)(840)629

Shelf life

Max. 24 months from the production date under normal storage conditions (+5°C to +30°C) and unopened can.

Additional Information

FOR PROFESSIONAL USE ONLY!

Always read the instructions.

IMPORTANT: This product contains hazardous substances at work, so it is necessary to always use/wear appropriate protective equipment. For further instructions, check the label on the product and safety data sheet. A person who uses the product for any purpose other than recommended in this technical data sheet, acts at his own risk. It is the user's responsibility to take all necessary steps to fulfil the local legislation.

Materials described are designed for application by professional, trained personnel using proper equipment and are not intended for sale to the general public.

Information and methods described are based on the best information and practices known to us and serve merely as guidelines for optimal use, without liability to performance, results, or fitness for any intended use. We do not accept any responsibility for the behaviour of the product or damage arising from the use of the product. Before using the product, the user must check if this is the latest version.

All products mentioned in this data sheet are trademarks owned by Silco.