

### Description

Universal high-performance polyester putty, characterized by its fine texture, ease of application and good sanding.




### Features & Benefits

- Excellent adhesion to galvanized and electro-zinc-coated metals, steel surfaces and aluminium,
- Very easy to spread,
- Non-porous, smooth surface,
- Excellent sanding,
- Specific weight: 1,8 kg/L;

### Substrate preparation

Surfaces to be treated must be clean, dry, rust-free and grease-free. Optimal adhesion can be achieved on well abraded surface. For aluminium and galvanized steel, use matting pad+matting paste to improve adhesion.

### Application data

|   |  |                   |                 |                                    |                           |
|---|--|-------------------|-----------------|------------------------------------|---------------------------|
|  | <p><b>Mixing ratio (by weight)</b></p> <table border="0"> <tr> <td>6050 B5 Multisoft</td> <td>100 (by weight)</td> </tr> <tr> <td>6065 Putty hardener</td> <td>2 – 3 % (do not overdose)</td> </tr> </table> <p>Mix the putty and hardener thoroughly until the colour is even.<br/>Use filler knife, plastic or rubber spatula for the application.</p> <p>Do not overdose! Excessive quantity of hardener can cause colour change on the topcoat and shorten the potlife. Hardener quantities below 2 % can result in prolonged drying time.</p> | 6050 B5 Multisoft | 100 (by weight) | 6065 Putty hardener                | 2 – 3 % (do not overdose) |
| 6050 B5 Multisoft   | 100 (by weight)  |                   |                 |                                    |                           |
| 6065 Putty hardener   | 2 – 3 % (do not overdose)  |                   |                 |                                    |                           |
|  | <p><b>Application</b></p> <table border="0"> <tr> <td>Usage temperature</td> <td>min 10 °C/50 °F</td> </tr> </table>   | Usage temperature | min 10 °C/50 °F |                                    |                           |
| Usage temperature   | min 10 °C/50 °F  |                   |                 |                                    |                           |
|  | <p><b>Drying</b></p> <table border="0"> <tr> <td>at 20 °C/68 °F</td> <td>20 – 25 min</td> </tr> <tr> <td>Pot life at (18-20°C)/(64,4-68 °F)</td> <td>3 – 4 min</td> </tr> </table> <p>It is not recommended to used IR or any other high temperature drying equipment if the temperature control is not possible, while the maximum temperature for drying of the putty is 45°C/113°F.</p>   | at 20 °C/68 °F    | 20 – 25 min     | Pot life at (18-20°C)/(64,4-68 °F) | 3 – 4 min                 |
| at 20 °C/68 °F  | 20 – 25 min  |                   |                 |                                    |                           |
| Pot life at (18-20°C)/(64,4-68 °F)  | 3 – 4 min  |                   |                 |                                    |                           |

## 6050 B5 Multisoft, Universal Soft Putty

Ver.: 2020-4



### Sanding /Only dry sanding

|                |             |
|----------------|-------------|
| First sanding  | P80 – P120  |
| Second sanding | P120 – P240 |

### Complementary products

6065 Putty hardener

6065-CT-0,06 Putty hardener (in combination with 1,65 L putty cartridge)

| Prod. Nr. | Description | Volume | Packaging Box |
|-----------|-------------|--------|---------------|
| 6050-0,5  | Beige       | 0,5 kg | 12            |
| 6050-1,8  | Beige       | 1,8 Kg | 6             |
| 6050-CT-3 | Beige       | 3 kg   | 4             |

The hardener is included in the packaging.

### VOC

VOC content: 2004/42/IIB (b) (250) <250

### Shelf life

Min. 12 months from the production date under normal storage conditions and unopened can.

### Additional Information

FOR PROFESSIONAL USE ONLY!

Always read the instructions.

**IMPORTANT:** This product contains hazardous substances at work so it is necessary to always use/wear appropriate protective equipment. For further instructions, check the label on the product and safety data sheet. A person who uses the product for any purpose other than recommended in this technical data sheet, acts at his own risk. It is the user's responsibility to take all necessary steps to fulfil the local legislation.

Materials described are designed for application by professional, trained personnel using proper equipment and are not intended for sale to the general public.

Information and methods described are based on the best information and practices known to us and serve merely as guidelines for optimal use, without liability to performance, results or fitness for any intended use. We do not accept any responsibility for the behaviour of the product or damage arising from the use of the product. Before using the product, the user must check if this is the latest version.

All products mentioned in this data sheet are trademarks owned by Silco d.o.o..