

6090 B9 Multi-Azure

High Performance Semi-Lightweight Putty

silco[®]

Rhapsody in blue for every Bodyshop.

- / Excellent sanding beginning with P 180 grit
- / Better surface assessment after sanding
- / Sanding after 20 minutes without paper clogging
- / Very easy to spread



6090 B9 Multi-Azure

High Performance Semi-Lightweight Putty

Drying time*

| | |
|----------------------------|--------|
| Dry to sand 20°C / 68 F | 20 min |
|----------------------------|--------|

| | |
|------------------------|-----------|
| Potlife 20°C / 68 F | 3 - 4 min |
|------------------------|-----------|

*Indicative times subject to amount of hardener/application/environment.

How to use?

Treated surface must be clean, dry, rust-free and grease-free. Optimal adhesion can be achieved on well abraded surface. Mix the putty and hardener thoroughly until the colour is even. Use filler knife, plastic or rubber spatula for the application. Do not overdose! Excessive quantity of hardener can cause colour change on the topcoat and shorten the potlife. Hardener quantities below 2% can result in prolonged drying time.

For further and updated information please refer to the TDS published on www.silco.si.

Product info

High performance semi-lightweight polyester putty can be used as filling or finishing putty. Blue colour enables better surface assessment after sanding due to perfect colour contrast between sanded and unsanded putty. It is easy to apply and to sand with fine-grained sanding papers, beginning P180 or P240. Sanding after 20 minutes from application is easy and without any paper clogging.

Packaging

Putty & Hardener

| Prod. Nr. | Content | Color |
|----------------------|---------|-----------|
| 6090-1 | 1 L | Azure |
| BPO Hardener 2 - 3 % | 50 g | Red paste |