

Description

Universal lightweight polyester putty. Its low specific weight enables it to fill irregularities and dents with significantly less product (by weight) in comparison with conventional putties.





Features & Benefits

- specific weight 1,27 kg/L (conventional putties \approx 2 kg/L)
- excellent adhesion to galvanized and zinc-coated metals, steel surfaces and aluminium
- very easy to spread, with high thixotropy
- non-porous, smooth surface
- excellent sanding, beginning with P120
- specific weight 1,27 kg/L

Substrate preparation

Surfaces to be treated must be clean, dry, rust-free and grease-free. Optimal adhesion can be achieved on well abraded surface.

Application data

	Mixing ratio	
	6100 Multimax	100 (parts by vol.)
	6065 Putty hardener	2 - 3 % (do not overdose)
	Mix the putty and hardener thoroughly until the colour is even.	
	Do not overdose! Excessive quantity of hardener can cause colour change on the topcoat.	
	Application	
	Usage temperature	min 10 °C/50 °F
	Drying	
	at 20 °C/68 °F	15 - 20 min
	Pot life at 20 °C/68 °F	3 - 4 min
	Sanding	
	Only dry sanding	P120 - 240

Complementary products

6065 Putty hardener

Prod. Nr.	Description	Volume	Packaging Box
6100-1,5	Beige	1.5 L	8

VOC

VOC 2004/42/IIB(c) (250) <250

Shelf life

Min. 12 months from the production date under normal storage conditions and unopened can.

Additional Information

FOR PROFESSIONAL USE ONLY!

Always read the instructions.

IMPORTANT: This product contains hazardous substances at work so it is necessary to always use/wear appropriate protective equipment. For further instructions, check the label on the product and safety data sheet. A person who uses the product for any purpose other than recommended in this technical data sheet, acts at his own risk. It is the user's responsibility to take all necessary steps to fulfil the local legislation.

Materials described are designed for application by professional, trained personnel using proper equipment and are not intended for sale to the general public.

Information and methods described are based on the best information and practices known to us and serve merely as guidelines for optimal use, without liability to performance, results or fitness for any intended use. We do not accept any responsibility for the behaviour of the product or damage arising from the use of the product. Before using the product, the user must check if this is the latest version.

All products mentioned in this data sheet are trademarks owned by Silco. All products mentioned in this data sheet are trademarks owned by Silco. For further questions please contact the company Silco d.o.o.