

Description

Super fast and easy to sand semilightweight polyester putty. The putty is sandable in 8 minutes (20°C) without paper clogging. Sanding is easy and fast.




Features & Benefits

- ready to sand in 8 minutes from application
- excellent adhesion to various substrates
- very easy to spread
- non-porous, smooth surface
- can be used as filling and fine putty
- excellent sanding, beginning with P150
- specific weight 1,45 kg/L

Substrate preparation

Surfaces to be treated must be clean, dry, rust-free and grease-free. Optimal adhesion can be achieved on well abraded surface. For aluminium and galvanized steel, use matting pad+matting paste to improve adhesion.

Application data

	<p>Mixing ratio</p> <table border="0"> <tr> <td>6110 B11 SFR Superfast</td> <td style="text-align: right;">100 %</td> </tr> <tr> <td>6065 Putty hardener</td> <td style="text-align: right;">3 % (by weight; do not under or overdose)</td> </tr> </table> <p>Mix the putty and hardener thoroughly until the colour is even. Do not overdose! Excessive quantity of hardener can cause colour change on the topcoat.</p>	6110 B11 SFR Superfast	100 %	6065 Putty hardener	3 % (by weight; do not under or overdose)
6110 B11 SFR Superfast	100 %				
6065 Putty hardener	3 % (by weight; do not under or overdose)				
	<p>Application</p> <table border="0"> <tr> <td>Usage temperature</td> <td style="text-align: right;">10 °C/50 °F</td> </tr> </table>	Usage temperature	10 °C/50 °F		
Usage temperature	10 °C/50 °F				
	<p>Drying</p> <table border="0"> <tr> <td>Dry to sand (20 °C/68 °F)</td> <td style="text-align: right;">8 – 10 min</td> </tr> <tr> <td>Pot life at (20 °C/68 °F)</td> <td style="text-align: right;">3 – 4 min</td> </tr> </table>	Dry to sand (20 °C/68 °F)	8 – 10 min	Pot life at (20 °C/68 °F)	3 – 4 min
Dry to sand (20 °C/68 °F)	8 – 10 min				
Pot life at (20 °C/68 °F)	3 – 4 min				



Sanding

Only dry sanding

P150 – P320

Complementary products

6065 Putty hardener, 50 g

6065-0,07 Putty hardener, 70 g

6065-CT-0,06 Putty hardener (in combination with 1,65 L putty cartridge)

Prod. Nr.	Description	Volume	Packaging Box
6110-1	White	1 L	6
6110-CT-1,65	White	1,65	4
6110-3	White	3 L	2

Hardener included in the packaging.

VOC

VOC 2004/42/IIB(c) (250) <120

Shelf life

Min. 12 months from the production date under normal storage conditions and unopened can.

Additional Information

FOR PROFESSIONAL USE ONLY!

Always read the instructions.

IMPORTANT: This product contains hazardous substances at work so it is necessary to always use/wear appropriate protective equipment. For further instructions, check the label on the product and safety data sheet. A person who uses the product for any purpose other than recommended in this technical data sheet, acts at his own risk. It is the user's responsibility to take all necessary steps to fulfil the local legislation.

Materials described are designed for application by professional, trained personnel using proper equipment and are not intended for sale to the general public.

Information and methods described are based on the best information and practices known to us and serve merely as guidelines for optimal use, without liability to performance, results or fitness for any intended use. We do not accept any responsibility for the behaviour of the product or damage arising from the use of the product. Before using the product, the user must check if this is the latest version.

All products mentioned in this data sheet are trademarks owned by Silco. All products mentioned in this data sheet are trademarks owned by Silco. For further questions please contact the company Silco d.o.o.