

6120 B12 Multi-Ultralight

silco[®]

High performance ultra-lightweight putty

The 6120 high performance ultra-lightweight putty is characterised by easy sanding as well as with high mechanical strength while maintaining good flexibility.

- / Excellent sanding beginning with P120 grit
- / High mechanical strength while maintaining good flexibility
- / Sanding after 20 minutes without paper clogging
- / Very easy to spread
- / Very low specific weight: ~0.9 kg/L



6120 B12 Multi-Ultralight

High performance ultra-lightweight putty

Drying time*

Dry to sand 20°C / 68 F	20 min
Potlife 20°C / 68 F	3–4 min

*Indicative times subject to amount of hardener/application/environment.

How to use?

Treated surface must be clean, dry, rust-free and grease-free. Optimal adhesion can be achieved on well abraded surface. For aluminium and galvanized steel, use matting pad+matting paste to improve adhesion. Mix the putty and hardener thoroughly until the colour is even. Use filler knife, plastic or rubber spatula for the application. Do not overdose! Excessive quantity of hardener can cause colour change on the topcoat and shorten the potlife. Hardener quantities below 2% can result in prolonged drying time.

For further and updated information please refer to the TDS published on www.silco.si.

Product info

This high-performance polyester putty is ultralight in weight. Characterised by easy sanding and with high mechanical strength and maintaining good flexibility, these characteristics minimize the risk of cracking even on larger areas. Having great adhesion to various substrates, it can be used for filling large voids and smaller imperfections. Because of its low specific weight, it is important to use it where low weight of used materials is expected (example: aircraft repair).

Packaging

Putty & Hardener

Prod. Nr.	Content	Color
6120-1	1 L	Yellow
6120-3	3 L	Yellow
BPO Hardener 2–3 %	50 g, 60 g, 70 g	Red paste