

6150 B15 Multi-Alu

Putty with aluminium

Polyester putty with aluminium particles for filling of deeper holes or dents in thicker layers without danger of cracking or sagging.

silco[®]

- / Strong adhesion, even to galvanized metals
- / Easy spreading and quick drying
- / Soft sanding
- / Non-sagging
- / Specific weight: 1.5–1.55 kg/L



6150 B15 Multi-Alu

Putty with aluminium

Drying time*

Dry to sand 20°C / 68 F	15–20 min
Potlife 20°C / 68 F	3–4 min

*Indicative times subject to amount of hardener/application/environment.

How to use?

Treated surface must be clean, dry, rust-free and grease-free. Optimal adhesion can be achieved on well abraded surface. Mix the putty and hardener thoroughly until the colour is even. Use filler knife, plastic or rubber spatula for the application. Do not overdose! Excessive quantity of hardener can cause colour change on the topcoat and shorten the potlife. Hardener quantities below 2% can result in prolonged drying time.

For further and updated information please refer to the TDS published on www.silco.si.

Product info

Polyester putty with aluminium particles for filling of deeper holes or dents in thicker layers without danger of cracking or sagging.

Packaging

Putty & Hardener

Prod. Nr.	Content	Color
6150-1	1 L	Aluminium
BPO Hardener 2–3 %	50 g, 60 g, 70 g	Red paste