

6150 Multi-Alu, Putty with Aluminium

Ver.: 2021-4

Description

Polyester putty with aluminium particles for filling of deeper holes or dents in thicker layers without danger of cracking or sagging.





Features & Benefits

- Strong adhesion, even to galvanized metals,
- Easy spreading and quick drying,
- Smooth spreading,
- Non-sagging;

Substrate preparation

Surfaces to be treated must be clean, dry, rust-free and grease-free. Optimal adhesion can be achieved on well abraded surface.

Application data

	<p>Mixing ratio</p> <table border="0"> <tr> <td>6150 Multi-Alu</td> <td>100 (by weight)</td> </tr> <tr> <td>6065 Putty hardener</td> <td>2 – 3 % (do not overdose)</td> </tr> </table> <p>Mix the putty and hardener thoroughly until the colour is even. Do not overdose! Excessive quantity of hardener can cause colour change on the topcoat.</p>	6150 Multi-Alu	100 (by weight)	6065 Putty hardener	2 – 3 % (do not overdose)
6150 Multi-Alu	100 (by weight)				
6065 Putty hardener	2 – 3 % (do not overdose)				
	<p>Application</p> <p>Usage temperature min. 10 °C/50 °F</p>				
	<p>Drying</p> <table border="0"> <tr> <td>at 20 °C/68 °F</td> <td>15 – 20 min</td> </tr> <tr> <td>Pot life at 20 °C/68 °F</td> <td>3 – 4 min</td> </tr> </table>	at 20 °C/68 °F	15 – 20 min	Pot life at 20 °C/68 °F	3 – 4 min
at 20 °C/68 °F	15 – 20 min				
Pot life at 20 °C/68 °F	3 – 4 min				
	<p>Sanding</p> <p>Only dry sanding P80 – 240</p>				

Recommendation

An additional coat of other finer putty is recommended before applying the primer-filler.

Complementary products

6065 Putty hardener

Prod. Nr.	Description	Volume	Packaging Box
6150	Aluminium	1 L	6

VOC

2004/42/IIB(b) (250) <150

Shelf life

Min. 12 months from the production date under normal storage conditions and unopened can.

Additional Information

FOR PROFESSIONAL USE ONLY!

Always read the instructions.

IMPORTANT: This product contains hazardous substances at work so it is necessary to always use/wear appropriate protective equipment. For further instructions, check the label on the product and safety data sheet. A person who uses the product for any purpose other than recommended in this technical data sheet, acts at his own risk. It is the user's responsibility to take all necessary steps to fulfil the local legislation.

Materials described are designed for application by professional, trained personnel using proper equipment and are not intended for sale to the general public.

Information and methods described are based on the best information and practices known to us and serve merely as guidelines for optimal use, without liability to performance, results or fitness for any intended use. We do not accept any responsibility for the behaviour of the product or damage arising from the use of the product. Before using the product, the user must check if this is the latest version.

All products mentioned in this data sheet are trademarks owned by Silco d.o.o..