

Description

Universal polyester putty with lower specific weight defined by its short drying time, fine creamy structure and smooth application without holes.





Features & Benefits

- specific weight 1,55 kg/L (conventional putties ≈2 kg/L)
- ready to sand in 15 minutes
- excellent adhesion to galvanized steel, aluminum and steel surfaces, glass-fibre reinforced plastics
- very easy to spread, with high thixotropy
- non-porous, smooth surface
- excellent sanding, beginning with P120
- can be used as filling and fine putty

Substrate preparation

Surfaces to be treated must be clean, dry, rust-free and grease-free. Optimal adhesion can be achieved on well abraded surface.

Application data

	<p>Mixing ratio</p> <table border="0"> <tr> <td>6700 MultiBlue</td> <td>100 %</td> </tr> <tr> <td>6065 Putty hardener</td> <td>2 – 3 % (by weight; do not overdose)</td> </tr> </table> <p>Mix the putty and hardener thoroughly until the colour is even. Do not overdose! Excessive quantity of hardener can cause colour change on the topcoat.</p>	6700 MultiBlue	100 %	6065 Putty hardener	2 – 3 % (by weight; do not overdose)											
6700 MultiBlue	100 %															
6065 Putty hardener	2 – 3 % (by weight; do not overdose)															
	<p>Application</p> <table border="0"> <tr> <td>Usage temperature</td> <td>min 5 °C/41 °F</td> </tr> </table>	Usage temperature	min 5 °C/41 °F													
Usage temperature	min 5 °C/41 °F															
	<p>Drying</p> <table border="0"> <tr> <td>at 20 °C/68 °F</td> <td>15 min</td> </tr> <tr> <td>Pot life at 20 °C/68 °F</td> <td>4 min</td> </tr> </table>	at 20 °C/68 °F	15 min	Pot life at 20 °C/68 °F	4 min											
at 20 °C/68 °F	15 min															
Pot life at 20 °C/68 °F	4 min															
	<p>Sanding</p> <table border="0"> <tr> <td>Only dry sanding!</td> <td>As filling putty</td> <td>As fine putty</td> </tr> <tr> <td></td> <td>First sanding</td> <td>P120</td> </tr> <tr> <td></td> <td>Re-sanding</td> <td>P120 – P240</td> </tr> <tr> <td></td> <td></td> <td>P120 – P180</td> </tr> <tr> <td></td> <td></td> <td>P180 – P240</td> </tr> </table>	Only dry sanding!	As filling putty	As fine putty		First sanding	P120		Re-sanding	P120 – P240			P120 – P180			P180 – P240
Only dry sanding!	As filling putty	As fine putty														
	First sanding	P120														
	Re-sanding	P120 – P240														
		P120 – P180														
		P180 – P240														

Complementary products

6065 Putty hardener

Prod. Nr.	Description	Volume	Packaging Box
6700	Blue	1,6 kg	8

VOC

VOC 2004/42/IIB(c) (250) <250

Shelf life

Min. 12 months from the production date under normal storage conditions and unopened can.

Additional Information

FOR PROFESSIONAL USE ONLY!

Always read the instructions.

IMPORTANT: This product contains hazardous substances at work so it is necessary to always use/wear appropriate protective equipment. For further instructions, check the label on the product and safety data sheet. A person who uses the product for any purpose other than recommended in this technical data sheet, acts at his own risk. It is the user's responsibility to take all necessary steps to fulfil the local legislation.

Materials described are designed for application by professional, trained personnel using proper equipment and are not intended for sale to the general public.

Information and methods described are based on the best information and practices known to us and serve merely as guidelines for optimal use, without liability to performance, results or fitness for any intended use. We do not accept any responsibility for the behaviour of the product or damage arising from the use of the product. Before using the product, the user must check if this is the latest version.

All products mentioned in this data sheet are trademarks owned by Silco. All products mentioned in this data sheet are trademarks owned by Silco. For further questions please contact the company Silco d.o.o.