

6880 Sprayplast

2K Polyester sprayable filler

2-component polyester based sprayable filler designed to easily fill irregularities on larger surfaces.

silco[®]

- / High filling power
- / Easy to apply, excellent flow
- / Sandable in 60 minutes from application
- / To be applied over bare metal, polyester putties/bodyfillers, glass-reinforced plastic or sanded original paints
- / Supplied with hardener



6880 Sprayplast

2K Polyester sprayable filler

Drying time*

Dry to sand 20°C / 68 F	45–60 min
Potlife 20°C / 68 F	20–30 min

*Indicative times subject to amount of hardener/application/environment.

How to use?

Treated surface must be clean, dry, sanded and degreased. The product should only be applied over:

- scuffed and degreased bare steel (not for use over Zinc, Aluminium, or plastic substrates)
- flattened glass fibre, polyester putties, wood
- completely dry epoxy primer (for best adhesion it is recommended to sand the epoxy primer)

Caution: Do not apply the putty directly on the paint primer, wash primer, galvanized steel, aluminium, acrylic, and nitrocellulose products. Polyester products have high sensitivity to water, therefore 6880 spray filler should be only dry sanded. Isolate with 1K/2K filler before overcoating with basecoats/topcoats. Painting equipment should be cleaned immediately after use.

For further and updated information please refer to the TDS published on www.silco.si.

Packaging

Putty & Hardener

Prod. Nr.	Content	Color
6880-1,5	1,5 kg	Grey

Supplied with 50 ml of liquid CHP hardener

Product info

2K polyester spray filler, for leveling small irregularities on larger surfaces.