

Description

90.310 UniMix 2K DTM 100 % Glossy Binder is used to produce polyurethane coatings based on PU 2K technology, which can be applied direct onto substrates and combine the features of a primer as well as the quality of the topcoat. It has no corrosion-inhibiting pigments therefore it is to be used only on corrosion resistant substrates like zinc-plated, aluminium, brass, etc. If used on other substrates be aware that corrosion may occur.

Features

- gloss levels of approximately 90 to 100 % (60° angle)
- one layer coating system
- good adhesion on various substrates (aluminium, galvanised steel, fibre reinforced plastic)
- can be applied with airless, air-assisted airless, conventional or HVLP methods
- high coverage power in combination with UniMix tinting system

Substrate preparation



Substrate

Sanding

Degreasing

Cast Iron: P80 - 120 (dry) SA2 ½ sandblasting

Bare steel : P80 - 120 (dry) or shot blast

Phosphated steel: Matting paste + matting cloth

Galvanized steel: Matting paste + matting cloth

Light alloys: Matting paste + matting cloth

Fiber reinforced plastic: P240 (dry)

All surfaces need to be thoroughly cleaned, dried and degreased with appropriate anti-silicone cleaner.

The product shows direct adhesion on metals without a previous primer application. Because of the variety of substrates is always better to perform some preliminary tests before final application.

It is recommended to use appropriate primer (epoxy, etch, etc.) to optimize adhesion and corrosion protection on aluminium and galvanized steel surfaces.


In case of sandblasting the surface, paint job must be done immediately after sand blasting.

In case of using the product on noncorrosion resistant surfaces you should be aware that corrosion may occur.


Mixing ratio

	<u>Airless</u>			<u>Spray gun</u>	
	Mixing ratio: (weight)	Mixed colour	1000	Mixed colour	1000
		2K Hardener	450	2K Hardener	450
		(9220/30/50/70)		(9220/30/50/70)	
		Thinner 7050/7070	0 - 45	Thinner 7050/7070	40 - 280
	Mixing ratio: (volume)	Mixed colour	2	Mixed colour	2
		2K Hardener	1	2K Hardener	1
(9230/9250/9270)			(9230/9250/9270)		
Thinner 7050/7070		0 – 5 %	Thinner 7050/7070	5 – 20 %	

Application

		<u>Airless</u>	<u>Spray gun</u>
	Spray gun set up:	9 - 11/120 – 140 bar	1,2 - 1,4 mm / 2 – 2,5 bar HVLP 2 bar
	Number of layers:	1 – 2	1,5 – 32
	Flash-off (20 °C/68 °F):	10 – 15 min	5 – 10 min
	Viscosity (DIN 4 at 20 °C/68 °F):	16 – 18 s	20 – 25 s
	Overcoating (20 °C/68 °F):	UniMix DTM coating is possible to overcoat with the same DTM coating in 15 minutes from first application or 6h after first application. When the material is completely dry (24h) the surface needs to be sandend.	

Drying

	Dust dry (20 °C/68 °F):	20 - 30 min
	Touch dry (20 °C/68 °F):	2 - 4 h
	Totally dry (20 °C/68 °F):	24 h
	Totally dry (60 °C/140 °F):	30 min
	Dry film thickness airless:	60 - 70 µm
	Dry film thickness spraygun:	50 - 60 µm
	Potlife (20 °C/68 °F):	2 h

Technical information

Theoretic yield:	8 m ² /kg of ready for use product gives 60 µm thick dry film.
Maximum chemical resistance:	after 7 days
Film appearance:	glossy; 90 – 100 % (60°angle); Gloss is lower in case of metallic colours
Adhesion (ASTM D 3359):	B = 5 on surfaces treated like above reported

VOC of mixed colour

2004/42/IIA(j)(500)<500

Health and safety

For Health, Safety and Environmental instructions please refer to relevant Safety Data Sheets and labels on the cans. Storage conditions should also be considered.

Article no.	Description	Volume	Packaging
90.310	UniMix 2K DTM 100 % Glossy Binder	/	20 kg

Additional information

FOR PROFESSIONAL USE ONLY!

Always read the instructions.

IMPORTANT: This product contains hazardous substances at work so it is necessary to always use/wear appropriate protective equipment. For further instructions, check the label on the product and safety data sheet. A person who uses the product for any purpose other than recommended in this technical data sheet, acts at his own risk. It is the user's responsibility to take all necessary steps to fulfil the local legislation.

Materials described are designed for application by professional, trained personnel using proper equipment and are not intended for sale to the general public.

Information and methods described are based on the best information and practices known to us and serve merely as guidelines for optimal use, without liability to performance, results or fitness for any intended use. We do not accept any responsibility for the behaviour of the product or damage arising from the use of the product. Before using the product, the user must check if this is the latest version.

All products mentioned in this data sheet are trademarks owned by Silco.