

silco®

silco®

903

HS Klarlack
HS prozorni lak
HS bezbojni lak
HS vernis transparent
HS trasparente
4.8 VOC clear coat

www.silco.si

GRUPO d.o.o., Šentupert 5a
3303 Gomilsko, Slovenska
Tel.: +386(0)2 703 31 60
info@grupa.si

- / Durable, yellowing-resistant finish

HS Klarlack
HS prozorni lak
HS bezbojni lak
HS vernis transparent
HS trasparente
4.8 VOC clear coat

www.silco.si

9030 X3 HS Clear Coat

HS Clear Coat

Product info

HS clear coat designed for efficient use, easy application and good finish. Combines fast drying with a good long lasting gloss, making it a reliable choice for car refinishing.

How to use

Ensure base coat is dry. Suitable for water- and solvent-based basecoats. Select the appropriate hardener according to the ambient temperatures. Apply two full coats; no thinner required.

Mixing ratio 2:1

Hardener	9083 / 9085 HS Hardener Fast / Standard
Drying time*	
20°C/68°F	8-14 h
60°C/140°F	20-30 min
Flash-off 20°C/68°F	5-10 min
Potlife 20°C/68°F	60-120 min

*Indicative times subject to hardener and thinner type/application/environment...

Packaging

9030 X3 HS Clear Coat
HS Clear Coat

Hardener / 9082 / 9083 / 9085 HS Hardener
HS Hardener - Mixing Ratio 2:1

Prod. Nr.	Content	Prod. Nr.	Content	Description
9030-1	1 L	9083-0,5 / 9083-2,5	500 ml / 2.5 L	Fast
9030-5	5 L	9085-0,2 / 9085-0,25 / 9085-0,75 / 9085-2,5	200 ml / 250 ml / 750 ml / 2.5 L	Standard