

9040 X4 HS Clear Coat

HS high gloss clear coat

silco[®]

- / Easy to apply
- / Excellent spillage
- / Fast drying
- / Excellent gloss
- / Long-lasting persistence and resistance to yellowing

www.silco.si



9040 X4 HS Clear Coat

HS high gloss clear coat

How to use?

Base coat should be fully dry. The product was tested on water basecoat and solvent basecoat.

Product info

High-quality HS clear coat, characterized by high gloss.

Mixing ratio 2:1

Hardener	Extra Fast 9220	Fast 9230	Standard 9250	Slow 9270
Drying time*				
20°C/68°F	~8 h	~10 h	~12 h	~14 h
60°C/140°F	~20 min	~23 min	~25 min	~30 min
IR	~10 min	~15 min	~15 min	~20 min
Flash-off 20°C/68°F	5–10 min			
Potlife 20°C/68°F	>60 min			
Thinner	No thinner is needed.			

*Indicative times subject to hardener and thinner type/application/environment...

Packaging

9040 X4 HS Clear Coat
HS high gloss clear coat

Prod. Nr.	Content
9040-1	1 L
9040-5	5 L

Hardener / 9220 - 9270 HS Hardener
HS Acrylic Hardener - mixing ratio 2:1

Prod. Nr.	Content	Description
9220-0,2 / 9220-0,5 / 9220-0,7 / 9220-2,5	200 ml / 500 ml / 700 ml / 2.5 L	Extra Fast
9230-0,2 / 9230-0,5 / 9230-0,7 / 9230-2,5	200 ml / 500 ml / 700 ml / 2.5 L	Fast
9250-0,2 / 9250-0,5 / 9250-0,7 / 9250-2,5	200 ml / 500 ml / 700 ml / 2.5 L	Standard
9270-0,5 / 9270-2,5	500 ml / 2.5 L	Slow