

9060 X6 UHS Clear Coat

Wide range clear coat

How to use?

Extra fast and fast hardeners are recommended for use on vertical surfaces. Light half coat followed by full closed coat without flash off can be used for spot and quick repairs. For all other repairs, use two full coats application method, with flash off between coats (5–10 min). Flash off time and drying time depends on the combination of the hardeners and thinners used.

For further and updated information please refer to the TDS published on www.silco.si.

Product info

The versatile high-quality acrylic UHS varnish is characterized by ease of use and excellent gloss of the painted surface.

Mixing ratio 2:1

Hardener	Extra Fast 9122	Fast 9123	Standard 9125	Slow 9127
Drying time*				
20°C/68°F	~5 h	~6 h	~7 h	~8 h
60°C/140°F	~15 min	~20 min	~25 min	~30 min
IR	~7 min	~9 min	~11 min	~15 min
Flash-off 20°C/68°F	5–10 min			
Potlife 20°C/68°F	20–30 min	30–40 min	50–60 min	50–60 min
Thinner	0–10 % (7030 Fast, 7050 Standard, 7070 Slow)			

*Indicative times subject to hardener and thinner type/application/environment...

Packaging

9060 X6 UHS Clear Coat
Wide range clear coat

Prod. Nr.	Content
9060-5	5 L

Hardener / 9122 - 9127 HS Hardener
HS Acrylic Hardener - mixing ratio 2:1

Prod. Nr.	Content	Description
9122-0,5 / 9122-2,5	500 ml / 2.5 L	Extra Fast
9123-0,5 / 9123-2,5	500 ml / 2.5 L	Fast
9125-0,33 / 9125-0,5 / 9125-1 / 9125-2,5	330 ml / 500 ml / 1 L / 2.5 L	Standard
9127-0,5 / 9127-1	500 ml / 1 L	Slow