

# 9110 X11 Spectrum Lite

UHS 420 Rapid Clear Coat

**silco**<sup>®</sup>

- / Fast drying
  - 15 minutes at 60°C
  - 3-4 hours at 20°C
- / Immediate polishing after cooling down
- / Superior gloss retention & UV protection
- / Very easy application & leveling

www.silco.si



# 9110 X11 Spectrum Lite

## UHS 420 Rapid Clear Coat

### Product info

Fast drying UHS clear coat characterized by its short drying time, high gloss, long-lasting gloss retention and perfect levelling.

### Mixing ratio 2:1

<b>Hardener</b>	<b>9122 / 9123 / 9125 / 9127 UHS Hardener</b> Extra Fast / Fast / Standard / Slow
<b>Drying time*</b>	
20°C/68°F	3-4 h
40°C/104°F	25-30 min
60°C/140°F	15 min
<b>Flash-off</b> 20°C/68°F	5-10 min
<b>Potlife</b> 20°C/68°F	60 min
<b>Thinner</b>	0-5 % (7050 Standard, 7070 Slow)

\*Indicative times subject to hardener and thinner type/application/environment...

### Packaging

**9110 X11 Spectrum Lite**  
UHS 420 Rapid Clear Coat

Prod. Nr.	Content
9110-1	1 L
9110-5	5 L

**Hardener / 9122 - 9127 UHS Hardener**  
UHS Acrylic Hardener - mixing ratio 2:1

Prod. Nr.	Content	Description
9122-2,5	2.5 L	Extra Fast
9123-0,5 / 9123-2,5	500 ml / 2.5 L	Fast
9125-0,33 / 9125-0,5 / 9125-1 / 9125-2,5	330 ml / 500 ml / 1 L / 2.5 L	Standard
9127-1 / 9127-2,5	1 L / 2.5 L	Slow