

9130 X13 Spectrum NG

UHS 420 rapid clear coat

silco[®]

- / Fast drying clear coat for complete resprays or spot repair
- / Flexible use in different ambient conditions, boosting auto shop productivity
- / Versatile application over various basecoat systems for different paint jobs
- / Very fast drying
 - 10 minutes at 60°C
 - 2.5 hours at 20°C
- / Immediate polishing after cooling down
- / Superior gloss retention & UV protection
- / Very easy application & leveling

www.silco.si



Contains 12% BIO based (sustainable) material

9130 X13 Spectrum NG

UHS 420 rapid clear coat

Product info

Premium UHS clear coat that combines fast drying times with effortless application and flawless leveling. With a potlife of over 60 minutes, it offers brilliant, long-lasting gloss and superior durability, including high resistance to yellowing.

This eco-conscious clear coat contains 12% bio-based raw materials, ensuring a sustainable choice while meeting VOC 420 compliance. It dries in just 10-15 minutes at 60°C or 3-4 hours at 20°C, providing flexibility for various working conditions. Compatible with hardeners 9330, 9350, and 9370 in a 2:1 ratio.

Mixing ratio 2:1

Hardener	Fast 9330	Standard 9350	Slow 9370
Drying time*			
20°C/68°F	3 h	3-4 h	5-6 h
40°C/104°F	25-30 min	25-30 min	30 min
60°C/140°F	10-15 min	15 min	15-20 min
Flash-off 20°C/68°F	5-10 min		
Potlife 20°C/68°F	60 min		
Thinner	0-5 % (7050 Standard, 7070 Slow)		

*Indicative times subject to hardener and thinner type/application/environment...

Packaging

9130 X13 Spectrum NG
UHS 420 rapid clear coat

Prod. Nr.	Content
9130-NG-1	1 L
9130-NG-5	5 L

Hardener / 9330 - 9370 UHS Hardener
UHS Acrylic Hardener - mixing ratio 2:1

Prod. Nr.	Content	Description
9330-0,5 / 9330-2,5	500 ml / 2.5 L	Fast
9350-0,5 / 9350-2,5	500 ml / 2.5 L	Standard
9370-0,5 / 9370-2,5	500 ml / 2.5 L	Slow