

9600 SFR X-Cure

UHS 420 ultra rapid clear coat

Ultra fast drying clear coat for perfect refinish results within minutes.

silco[®]

- / Only 3 minutes at 60°C
- / Only 50 minutes at 20°C
- / Very easy application with 1:1 mixing ratio
- / Immediate polishing after cooling down
- / Perfect gloss retention & UV protection
- / In the base coat no hardener/activator is needed

www.silco.si



9600 SFR X-Cure

UHS 420 ultra rapid clear coat

Mixing ratio 1:1

Hardener	Standard 9650	Slow 9670
Drying time*		
20°C/68°F	~50 min	~60 min
60°C/140°F	~3 min	~5 min
IR	~3 min	~5 min
Flash-off 20°C/68°F	<5 min	<5 min
Potlife 20°C/68°F	60 min	60 min
Thinner	No thinner needed	

*Indicative times subject to hardener type/application/environment...

How to use?

Use of slow hardener is recommended in case of higher temperatures in combination with larger surfaces. Light half coat followed by full closed coat without flash off can be used for spot and quick repairs. For all other repairs, use two full coats application method, with max. 5 minute flash off between coats.

For further and updated information please refer to the TDS published on www.silco.si.

Product info

Highly productive UHS clear coat X-Cure is characterised by outstandingly short drying times when baking (3–5 min/60°C) or when air drying (50–60 min/20°C). Polishing is possible immediately after cooling. Short drying times allow more turnover of vehicles and decreased manpower costs. Additionally, fast drying without oven baking allows fuel and electricity savings.

Packaging

9600 SFR X-Cure
UHS 420 ultra rapid clear coat

Prod. Nr.	Content
9600-1	1 L
9600-2,5	2.5 L
9600-5	5 L

Hardener / 9650 - 9670 UHS Hardener
UHS Acrylic Hardener - mixing ratio 1:1

Prod. Nr.	Content	Description
9650-1 / 9650-2,5	1 L / 2.5 L	Standard
9670-2,5	2.5 L	Slow